



## RECTANGULAR 45° PIPE

Material Description	Dimensions				Material Thickness
	A	B	C	D	
AAP-45-35 Rectangular 45° Pipe	3"	5"	4"	6"	1/8"
AAP-45-39 Rectangular 45° Pipe	3"	9"	4"	6"	3/16"
AAP-45-312 Rectangular 45° Pipe	3"	12"	4"	8"	3/16"
AAP-45-317 Rectangular 45° Pipe	3"	17"	4"	11"	3/16"
AAP-45-327 Rectangular 45° Pipe	3"	27"	4"	16"	3/16"
AAP-45-414 Rectangular 45° Pipe	4"	14"	4"	11"	3/16"
AAP-45-420 Rectangular 45° Pipe	4"	20"	4"	16"	3/16"

**ENGINEERING DATA** Advanced Aquaduck cold-formed, welded, hollow rectangular steel pipe and fittings are produced in accordance with mechanical and chemical property requirements of ASTM specification A500 grade "B". Tensile Strength minimum: 58,000 psi. Yield Point minimum: 46,000 psi.

**COATING** Asphalt emulsified with bentonite clay. Complies with ASTM D-1227-87 Type III and ASTM D-1187-82 Type I.

**COATING APPLICATION** Immersion

**METHOD CONNECTION** Rectangle to rectangle connections; lead and oakum, lead wool, epoxy bonding method, or other approved method. Cast iron or plastic pipe connection shall use cast iron or plastic to steel, no-hub style couplings.

Representative: